भारतीय मानक Indian Standard

IS 3937 (Part 1): 2022

तार की रस्सियों की सॉकेटिंग के लिए संस्तुतियाँ

भाग 1 ज़िंक सहित सॉकेटिंग

(दूसरा पुनरीक्षण)

Recommendations for Socketing of Wire Ropes

Part 1 Socketing With Zinc

(Second Revision)

ICS 77.140.65

© BIS 2022



भारतीय मानक ब्यूरो BUREAU OF INDIAN STANDARDS मानक भवन, 9 बहादुर शाह ज़फर मार्ग, नई दिल्ली - 110002 MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG NEW DELHI - 110 002

 $\underline{www.bis.gov.in}$

www.standardsbis.in

FOREWORD

This Indian Standard (Part 1) (Second revision) was adopted by the Bureau of Indian Standards, after the draft finalized by the Wire Ropes and Wire Products Sectional Committee had been approved by the Mechanical Engineering Division Council.

This standard was first published in 1967 and revised in 1974. This standard is being revised again to keep pace with the latest technological developments and international practices. In this revision, the following major changes have been made:

- 1) A reference clause has been added mentioning the latest version of all the referred standards.
- 2) Editorial corrections have been done.

This standard on Socketing with Zinc is one of the series of standards on Socketing. Other parts of this standard are:

```
IS 3937 (Part 2): 1974 — Socketing with white metal (First Revision) IS 3737 (Part 3): 1993 — Socketing with resins.
```

The composition of the committee responsible for the formulation of this standard is given in Annex A.

For the purpose of deciding whether a particular requirement of this standard is complied with the final value, observed or calculated, expressing the result of a test or analysis shall be rounded off in accordance with IS 2:2022 'Rules for rounding off numerical values (second revision)'. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

Indian Standard

RECOMMENDATIONS FOR SOCKETING OF WIRE ROPES PART 1 SOCKETING WITH ZINC

(Second Revision)

1 SCOPE

Covers the procedure to be adopted for socketing of stranded wire ropes by molten zinc so that maximum safety is assured.

2 REFERENCES

The standards listed below contain provisions which, through reference in this text, constitute provisions of this standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this standard are encouraged to investigate the possibility of applying the most recent editions of the

standards listed below. In case the standards are to be referred in this clause they are to be listed as follows:

IS No Title

209 : Specification for zinc (fourth 1992 revision)

3 MATERIAL

The material chosen for socketing shall be zinc conforming to IS 209: 1992. The composition, melting point and pouring temperature of the metal are given in Table 1

Table 1 Composition, Melting Point and Pouring Temperature of Socketing Metal(Clause 3)

Sl No.	Grade	Composition Min Zn	Approximate Melting Point	Pouring Temperature
(1)	(2)	(3)	(4)	(5)
i)	Zn 99.95 of IS 209:1992	99.95 percent	420°C	450 to 480°C

4 PROCEDURE

4.1 Carefully seize the wire rope just below the point where it is to be cut with tinned or galvanized seizing wires of the sizes given in Table 2 and cut the wire rope.


Table 2 Dimensions of Seizing Wire (Clause 4.1)

Sl No.	Nominal Diameter of Wire Rope	Seizing Wire Diameter
	mm	mm
(1)	(2)	(3)
i)	8 to 24	1.0
ii)	25 to 36	1.5
iii)	38 to 56	2.0

- **4.2** Seize the rope with soft iron wire for a length XY (Fig. 1) equal to twice the diameter of the rope, leaving the rope end free of this seizing YZ equal to the length of the socket barrel less half a rope diameter.
- **4.3** Thread the socket onto the rope and push it along out of the way.
- **4.4** Unlay the rope end beyond the seizing, separate all the wires out into a brush, taking care that the wires are not bent by more than 45. The fibre core, if any should be removed or cut as deep into the brush as possible. (Fig. 2)
- **4.5** Clean the basket and brush to remove all grease and dirt; a degreasing agent or trichloroethylene may be used. Petrol or

paraffin is not recommended. When using a degreasing agent, the fluid should be liberally used and worked well into the throat of the brush. Remove the fluid and lubricant emulsion by washing off with hot water. Shake off the surplus water and dry the brush, it is essential that it is held downwards in the vertical position to prevent degreasing fluid, water or solvent being trapped in the throat of the brush or percolating back into the main body of the rope forming a source of corrosion. Trichloroethylene or other organic solvents shall only be used in well ventilated conditions. When used indoors, purpose designed equipment shall be used. After cleaning, the wires should first be dried and protected from contamination and also kept clear and dry until the molten metal is poured.

4.6 The cleaned brush end is drawn into position in the socket basket with the ends of the brush flush with the end of the basket. The socket is fixed upright in a soft jawed vice or clamps with the large end up. Seal the junction of the rope of the socket with asbestos yarn or asbestos fibre to prevent the escape of molten zinc. Care should be taken that the axes of the wire rope and the socket are in line and the rope is sensibly vertical over a length of at least 24 times the wire rope diameter from the socket end.



SOCKETING WITH MOLTEN ZINC

- **4.7** Gradually and evenly heat the socket around the outside circumference by a blow lamp or by any other suitable method so that the basket surface temperature is raised between 100 and 200°C.
- **4.8** The molten zinc at the proper pouring temperature specified in Table 1 is poured into the heated socket (Fig. 3). Before pouring, dross accumulated on the surface of the bath should be skimmed off. Care should be taken that only the clean bright fluid metal at the right temperature free from dross is poured into the socket. The ladle should be of sufficient capacity to hold the molten zinc to fill the socket in one filling. Pouring should be continuous, uniform until the metal completely fills the socket. To ensure that the poured metal penetrates between the wires completely, tap the socket lightly, if necessary, while the molten zinc is being poured.
- **4.9** After pouring the metal, allow the socket to cool gradually and do not disturb the socket till the metal is fully set and the socket cools to air temperature. The rope adjoining the socket shall then be carefully cleaned and treated with preservative dressing. After cooling, it is recommended that the seizing at the throat be removed enough to show any' broken wire that may appear adjacent to the throat during service.
- **4.10** It is not necessary to use any flux with zinc, however, as the molten zinc has a tendency to oxidize in contact with air, it is necessary to protect the surface of the molten zinc with bone charcoal to prevent oxidation. While molten zinc is being poured into the socket, care has to be taken that none of the charcoal is carried along with the molten zinc into the socket.

ANNEX A

(Foreword)

COMMITTEE COMPOSITION

Wire Ropes and Wire Products Sectional Committee, MED 10

Organization	Representative(s)		
Directorate General of Mines Safety, Dhanbad	Shri D B Naik (<i>Chairman</i>)		
Dhanbad	SHRI VIJAY BARAPATRE (Alternate)		
Bharat Coking Coal Limited, Dhanbad	SHRI P. K. SINHA		
	SHRI R. K. MUNSHI (Alternate)		
Bharat Wire Ropes Limited, Mumbai	SHRI MAHENDER SINGH ARORA		
	SHRI MAYANK MITTAL (Alternate)		
Central Institute of Mining and Fuel	DR MANOJ KUMAR SINGH,		
Research, Dhanbad	DR DEBASISH BSSAK (Alternate)		
Directorate General of Quality Assurance, New Delhi	COL K. SURESH		
New Deim	LT COL JA VORA (Alternate)		
Directorate General FAC Advice Service	SHRI B N JHA		
and Lab Institute, Mumbai	SHRI AMIT GOLA		
Directorate General of Aeronautical Quality Assurance, New Delhi	SHRI SANTOSH INGOLE		
Eastern Coalfields Limited, Kolkata	Dr. Manas Kumar		
Hindustan Zinc Limited, Dariba	SHRI RAKESH SINGHVI		
	SHRI SUFAL MEHROTRA (Alternate)		
Maccaferri Environment Solutions Pvt.	SHRIMATI MINIMOL KORULLA		
Limited, Navi Mumbai	SHRI RUDRA BUDDHABHATTI (Alternate)		

Organization Representative(s)

Manganese Ore Limited, Nagpur SHRI S C RAI

SHRI ATUL SHARMA (Alternate)

SHRI ASHWINI BAGHELE (ALT*ernate-II*)

Shri Rudra Budhbhatti (Alternate

III)

Ministry of Shipping, New Delhi Shri Anil Pruthi

SHRI RAMJI SINGH (Alternate)

Nanda and Miller Co., Kolkata Shri J P Goenka

National Test House, Kolkata Shri Suresh Parwal

SHRI ANGAD VERMA (Alternate)

Oil and Natural Gas Commission, New

Delhi

SHRI RAKESH KUMAR SRIVASTAVA

SHRI RITUJIT HAZARIKA (Alternate)

Orient Wire Ropes, Indore Shri Sameer Golwelkar

SHRI SHISHIR AKARTE (Alternate)

South Eastern coalfields Limited, Bilaspur Shri Kapil K. Rai

SHRI D. BHATTACHARJEE (Alternate)

Tata Steel Limited, Dhanbad Shri Soumendu Majhi

The Shipping Corporation of India Limited,

Mumbai

SHRI G. S. BHALLA

CAPT R.MODI (Alternate)

Usha Martin Industries Limited, Ranchi Shri Subrata Dutta

SHRI SANDEEP JAISWAL (Alternate)

BIS Directorate General SHRI RAJNEESH KHOSLA, Scientist 'E' And

Head (MED) [Representing Director General

(Ex-Officio)]

Member Secretary

Shri Sandeep Keshav

Scientist 'C' (MED), BIS

This Pade has been Intentionally left blank

This Pade has been Intentionally left blank

Bureau of Indian Standards

BIS is a statutory institution established under the *Bureau of Indian Standards Act*, 2016 to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Head (Publication & Sales), BIS.

Review of Indian Standards

Amendments are issued to standards as the need arises on the basis of comments. Standards are also reviewed periodically; a standard along with amendments is reaffirmed when such review indicates that no changes are needed; if the review indicates that changes are needed, it is taken up for revision. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition by referring to the website-www.bis.gov.in or www.standardsbis.in.

This Indian Standard has been developed from Doc No.: MED 10 (18779).

Amendments Issued Since Publication

Amend No.	Date of Issue	Text Affected	

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002

Telephones: 2323 0131, 2323 3375, 2323 9402 Website: www.bis.gov.in

_	-	
Regional Offices:		
Central	: 601/A, Konnectus Tower -1, 6 th Floor, DMRC Building, Bhavbhuti Marg, New Delhi 110002	2323 7617
Eastern	: 8 th Floor, Plot No 7/7 & 7/8, CP Block, Sector V, Salt Lake, Kolkata, West Bengal 700091	2367 0012 2320 9474
Northern	: Plot No. 4-A, Sector 27-B, Madhya Marg, Chandigarh 160019	{ 265 9930
Southern	: C.I.T. Campus, IV Cross Road, Taramani, Chennai 600113	2254 1442 2254 1216
Western	: Plot No. E-9, Road No8, MIDC, Andheri (East), Mumbai 400093	{ 2821 8093

Branches: AHMEDABAD. BENGALURU. BHOPAL. BHUBANESHWAR. CHANDIGARH. CHENNAI. COIMBATORE. DEHRADUN. DELHI. FARIDABAD. GHAZIABAD. GUWAHATI. HIMACHAL PRADESH. HUBLI. HYDERABAD. JAIPUR. JAMMU & KASHMIR. JAMSHEDPUR. KOCHI. KOLKATA. LUCKNOW. MADURAI. MUMBAI. NAGPUR. NOIDA. PANIPAT. PATNA. PUNE. RAIPUR. RAJKOT. SURAT. VISAKHAPATNAM.